

20 Block - Thickness 20

Technical characteristics

The 20 cm block is very versatile and is specifically suited to new constructions and extensions. This masonry block is compatible with all construction systems (wood frame, post-beam system, classic construction, etc.). This breathable and insulating block guarantees excellent thermal phase shift in summer and winter alike. When used for interior partitions, it offers very high acoustic comfort. It can also be used in interior and exterior insulation of existing buildings that require very high thermal performance.

	Value	Unit	Standard
Thickness	20	cm	
Modular dimensions	60 x 30	cm	
Number of blocks per m ²	5,5	blocks/m²	
Maximum block weight	16,5	kg	
Weight of the masonry	0,98	kN/m²	
Adhesive consumption	7,8	kg/m²	
Dry thermal resistance	3	m²K/W	EN 12667
Thermal resistance at 50% RH	2,82	m²K/W	EN 12667
Phase shift λ	0,071	W/mK	EN 12667
Phase shift	13,1	h	ISO 13786
Sound reduction index* Rw	40 (-1 ;-5)	dB	ISO 10140-2
Acoustic absorption coefficient α	0,85		EN ISO 354: 2003
Equivalent air layer thickness Sd	0,56	m	EN ISO 12572
Water vapour resistance factor µ	2,8		EN ISO 12572
Compressive strength	0,22	MPa	EN 772-1
Compressive strenght at ULS fd	0,099	MPa	
Reaction to fire	B, s1, d0		NF EN 13501-1
Resistance to fire with render	EI 120	min	EN 1364-1

^{*} Coated hempblok 15mm on one side – Simulated value

Advantages

- Summer and winter comfort
- Significant thermal phase-shift
- Quick and easy implementation
- Significant durability of the insulation and its performance

Packaging

	Value	Unit	
Dimensions of a pallet	120 x 100 x 114	cm	
Maximum weight of a pallet	521	kg	
Number of blocks per pallet	30	blocks/pallet	
Number of m² per pallet	5,4	m²/pallet	
Number of blocks per m ²	5,5	blocks/m²	
	Storage		
Pallet with shelf stored outside	6 months		
Open pallet and exterior wall in progress	3 months		
Masonry under completed roof	1 year with a maximum of 1 winter		

Applications





^{**} Hemp block masonry plastered on the fire side

^{***} Insignificant considering a damping of more than 300